

tesa® 8466

150µm double sided translucent HAF non-woven mounting tape

PRODUCT INFORMATION

Product Description

tesa® HAF 8466 is a copolyester based thermoplastic bonding film. This translucent double sided tape has a non-woven backing. It is protected by a strong paper liner.

tesa® HAF 8466 is free of halogen and compliant with current ROHS standards.

At room temperature tesa® HAF 8466 is not tacky. It is activated by heat while applying slight pressure.

Special Features:

- Reliable and ageing resistant bonds
- Very high performance on large bonding areas
- Low bonding pressure required
- Low oozing ratio & excellent process ability due non-woven backing
- Excellent shock resistance
- Bonds remain elastic

Main Application

tesa® HAF 8466 is especially recommended for bonding of metal components to various plastic or metal surfaces, e.g. SUS or AL to PC, PMMA or ABS:

- Bonding of decorative metal components
- Bonding of logo to housing
- Fabric bonding in accessories

Technical Data

■ Backing material	non-woven	■ Type of adhesive	copolyester
■ Colour	translucent	■ Type of liner	glassine
■ Total thickness	150 µm	■ Bonding strength	5 N/mm ²

For latest information on this product please visit <http://l.tesa.com/?ip=08466>

Page 1 of 2 / As of 07/10/14

tesa SE

Quickbornstraße 24
20253 Hamburg
Germany
Phone: +49 (40) 4909 101

tesa SE
A Beiersdorf Company

<http://www.tesa.com>

tesa tape inc.

5825 Carnegie Boulevard
Charlotte, N.C. 28209
United States of America
Phone: +1 (704) 554 0707
Fax: +1 (704) 553 5634
<http://www.tesatape.com>

tesa tape Asia Pacific Pte. Ltd.

9 North Buona Vista Drive
#04-01 The Metropolis
Tower 1
Singapore 138588
Tel: +65 6697 9888
Fax: +65 6659 6390
<http://www.tesa-asia.com>

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to advise you.

Additional Info

Technical recommendations: tesa® HAF 8466 is not self adhesive. It is activated by heat while applying slight pressure.

The following values are recommendations for machine parameters to start with:

1. Pre-lamination: During pre-lamination, the adhesive tape is laminated onto the metal substrate. This step does not affect the shelf life time of the adhesive tape. Pre-laminated components can be stored over the same period of time as the adhesive tape.

Machine setting:

- Temperature¹ 100 – 140 °C
- Pressure² 2 – 5 bar
- Time 2 – 5 s.

2. Bonding: Remove the liner from tape after pre-lamination step. Place the metal part onto the plastic component. Apply sufficient temperature through the metal part while applying pressure for the bonding time to reach sufficient bonding strength.

Machine setting:

- Temperature¹ 125 – 150 °C
- Pressure² 2 – 5 bar
- Time 5 – 15 s.

To achieve optimum performance a cooling step (while applying pressure) directly after the bonding step is recommended.

¹ 'Pre-lamination' and 'Bonding' temperature refer to the data that is measured at the surface of heating jig.

² 'Pre-lamination' and 'Bonding' pressure refer to the force that is transformed from jig surface directly to the bonding area.

Bonding strength values were obtained under standard laboratory conditions. (Material: AL & PC test specimen / Bonding conditions: Temperature = 150 °C; Pressure = 5 bar; Time = 7 sec).

To reach maximum bonding strength surfaces should be clean and dry. Storage conditions according to tesa® HAF shelf life concept.

For latest information on this product please visit <http://l.tesa.com/?ip=08466>

Page 2 of 2 / As of 07/10/14

tesa SE

Quickbornstraße 24
20253 Hamburg
Germany
Phone: +49 (40) 4909 101

tesa SE
A Beiersdorf Company

<http://www.tesa.com>

tesa tape inc.

5825 Carnegie Boulevard
Charlotte, N.C. 28209
United States of America
Phone: +1 (704) 554 0707
Fax: +1 (704) 553 5634
<http://www.tesatape.com>

tesa tape Asia Pacific Pte. Ltd.

9 North Buona Vista Drive
#04-01 The Metropolis
Tower 1
Singapore 138588
Tel: +65 6697 9888
Fax: +65 6659 6390
<http://www.tesa-asia.com>

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to advise you.